

ADFOAM ULTIMATE 1815

Straw grade polyurethane insulating foam-15°C

DESCRIPTION

ADFOAM ULTIMATE 1815 is a one-component, self-expanding, straw grade ready to use polyurethane foam. It is used for insulation on windows, doors, curtain wall perimeters or any other gaps that need to be filled. It can be used as low as -15°C. ADFOAM ULTIMATE 1815 meets CAN/ULC S102 and ASTM E84 (UL R26654). It contains CFC-free propellants, which are completely harmless to the ozone layer. ADFOAM ULTIMATE 1815 reaches R5 (thermal resistance) per square inch insulation rate. It adheres to most common construction materials and can also be used in plumbing and electrical applications.

PHYSICAL PROPERTIES

Tests	Standard	Results	
Base		Single component polyurethane	
Color		Champagne	
Consistency		Stable foam, thixotropic	
Curing system		Moisture cure	
Skin formation time at 20°C (68°C) and 65% HR		±8 minutes	
Drying time at 20°C (68°F) and 65% RH		Dust-free after 20-25 minutes	
Curing rate		See chart below	
Yield		See chart below	
Shrink		None	
Post expansion		None	
Cellular Structure		70-80% closed cell	
Specific gravity		±24kg/m ³ (extruded, fully cured)	
Temperature resistance		-40°C to +90°C (-40°F to 194°F) when cured	
Fire Class	DIN 4102-part 2	B3	
Insulation factor		33mW/m. K	
Shear strength	DIN 53427	17 N/cm ²	
Compression strength	DIN 53421	3 N/cm ²	
Bowing strength	DIN 53423	7 N/cm ²	
Water absorption	DIN 53429	Approximately 1% Vol	
V.O.C.		173 g/L	

PRODUCT CHARACTERISTICS

- Minimal expansion, will not cause any distortion
- Excellent adhesion on most substrates (except Teflon, PE, and PP)
- High thermal and acoustical insulation
- Very good filling capacities
- Excellent mounting capacities
- Excellent stability (no shrink or post-expansion)
- Does not slump at low temperature
- Can be applied at low temperatures
- Very precise application due to the foam gun system •



ADFOAM ULTIMATE 1815 Straw grade polyurethane insulating foam-15°C

APPLICATIONS

- Installation of window and doorframe
- Filling cavity
- Sealing of all openings in roof construction
- Creation of a soundproof screen
- Mounting and sealing of window and doorframe
- Connecting insulation materials and rood constructions
- Improving thermal insulation in cooling system

SPÉCIFICATIONS

CAN/ULC S102



Caulking and sealants surface burning characteristics applied to inorganic reinforced cement board. Flame spread: 30

Cmake developed

Smoke developed: 50

*Tested as applied in two 25.4mm (1 inch) diameter beads 203.2mm (8 inches) on center covering 11.1% of the exposed test sample area.

ASTM E84



Caulking and sealants surface burning characteristics applied to inorganic reinforced cement board. Flame spread: 15

Smoke developed: 35

*Tested as applied in two 25.4mm (1 inch) diameter beads 203.2mm (8 inches) on center covering 11.1% of the exposed test sample area.

METHOD OF USE

All surfaces must be free of dust, oil, grease, frost, or any other contaminant. Clean all surfaces with ADFOAM CLEANER 500. Let evaporate 20 minutes prior to ADFOAM ULTIMATE 1815 application. Shake the aerosol can for at least 30 seconds. Fit the gun on the adapter. Moisten surfaces with a water spray prior to application (only when temperature > 0°C (32°F). During installation, doors and windows should be leveled, squared, and mechanically fastened to avoid distortion of the frame. Fill holes and cavities at 65% as the foam will expand. The size of a foam bead should be between 1/8 and 3 inches. Repeat shaking regularly during application. If you must work in layers repeat moistening after each layer (only when temperature >0°C (32°F). Fresh foam can be removed using ADFOAM CLEANER 500. Cured foam can only be removed mechanically. For later utilization, when there is still some foam inside the can, keep the can screwed on the gun. Cured foam may be trimmed or sanded. Cured foam must be protected from UVB radiation by painting or applying a top layer of sealant (silicone or hybrid sealant). Application temperature: -15°C (-5°F) to 35°C (95°F).



ADFOAM ULTIMATE 1815 Straw grade polyurethane insulating foam-15°C

YIELD AND CURING TIME

Temperature of the can: 18°C (64°F)

Temperature	20°C (68°F)	0°C (32°F)	-15°C (23°F)	-10°C (-14°F)
Cured foam volume	± 35 liters ± 2136 in ³	± 30 liters ± 1830 in ³	± 28 liters ± 1709 in ³	± 24 liters ± 1465 in ³
Curing time in joint of 3cm x 3cm	1 hour	3 to 6 hours	6 to 9 hours	9 to 12 hours

PACKAGING

750ml (26 oz) aerosol can (12 per box)

SHELF LIFE

12 months from date of production, in unopened packaging in a cool and dry storage place at temperatures between 10°C (50°F) and 25°C (77°F). High humidity and storage below or above these temperatures will shorten shelf life. Always store and transport can with the valve pointed upwards.

HANDLING AND SAFETY

Apply the usual industrial hygiene. Wear gloves and safety goggles. Remove cured foam by mechanical means only, never burn away. Consult the SDS (Safety Data Sheet) for more information. If you need additional information, do not hesitate to contact your technical representative. Always test product on your application prior to use. For industrial use only.

IMPORTANT

READ CAREFULLY

The information and recommendations contained herein are derived from our research and information from other reliable sources. This data applies only to our products and not when used with other products. We believe in the reliability of our information. However, no guarantee is offered to that effect. It is the responsibility of the buyer to verify this data according to their own operating conditions to ensure that they conform to the purpose for which the product is intended, even before using it.

THE WARRANTY OFFERED BY ADFAST SHALL BE LIMITED TO THE REPLACEMENT OR REIMBURSEMENT OF THE PRODUCT IF THEY HAVE BEEN DEFECTIVE. NO OTHER IMPLIED OR EXPRESS WARRANTY APPLIES. ADFAST DISCLAIMS ANY OTHER LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.