

# **ADSEAL FC 4570 SERIES**

FAST NEUTRAL CURE SILICONE

#### DESCRIPTION

ADSEAL FC 4570 SERIES is a one-component fast cure sealant/adhesive that vulcanizes as durable, elastic rubber silicone in contact with ambient humidity. Due to its rheological and non-sagging characteristics, it can be applied above the head, over the joints and on surfaces of vertical and horizontal walls.

Due to its fast cure system, ADSEAL FC 4570 SERIES is use in high speed production line.

ADSEAL FC 4570 SERIES adheres to glass, most types of wood, clean metals, silicone resins, ceramics, vulcanized silicone, synthetic and natural fibers and many painted surfaces (Validate with your representative) or certain plastics.

ADSEAL FC 4570 SERIES CAN NOT BE PAINTED.

Due to its vulcanization system in contact with moisture, the depth of the bead should not exceed 1/2 " (13 mm), otherwise the sealant cannot vulcanize completely. Minimum movement joint should be1/4" x 1/4".

### LIMITATIONS

- Not designed for permanent immersion joints
- Where the sealant is encapsulated and does not have access to ambient humidity
- In contact with strongly acidic or alkaline products
- Not designed for horizontal seals with circulation
- Joint less than 1/4 "(6 mm) wide and deep

## **PHYSICAL PROPERTIES**

Uncured	
Appearence	Pasty
Color	Translucent (4571), black (4573) and white (4572) Special colors upon request
Density	1.012 (translucent) 1.3 to 1.4 (colored)
Tack free time	2 – 7 minutes
Extrusion rate (50 psi / nozzle diameter 5mm)	75 to 250 g/min

Cured	
Shore A hardness	38 (translucent) 48 – 55 (colored)
Elongation at break	568% (translucent) 700% - 800% (colored)
Tensile strength	156 psi (translucent) 300 - 350 psi (colored)
Lap shear (on aluminum)	111 psi (translucent) 100 - 130 psi (colored)

### APPLICATION

- Primary bedding compound for glass in wood, vinyl and aluminum window sash
- Back bedding for doors and windows
- Every other applications that require fast cure silicone





# **ADSEAL FC 4570 SERIES**

FAST NEUTRAL CURE SILICONE

#### SURFACE PREPARATION

Surface must be free of dust, oil, grease, frost or any other contaminant. Use ADSEAL CLEANER 6003 to clean all surfaces. Let it evaporate 20 minutes before sealant application. Ensure that the backer rod ADSEAL BR-2600 is friction fitted properly and ADSEAL PRIMER MK60095 have been applied if necessary. When using ADSEAL PRIMER MK60095 let evaporate for 20 minutes prior to ADSEAL FC 4570 SERIES application.

#### METHOD OF USE

ADSEAL FC 4570 SERIES is easy to apply with conventional manual, pneumatic or electric caulking equipment. Shape the sealant bead with the ADSEAL TOOLING KIT before skin formation. In order to facilitate the work, the shaping can be done with a solution of 5% clear dish soap and 95% water. Dip the ADSEAL TOOLING KIT into the solution. Avoid applying solution directly to the sealant. The use of this solution may reduce sealant adhesion if used in an abusive manner. Uncured sealant can be clean with a solvent such as mineral spirit.

#### PACKAGING

- 304ml cartridge
- 600ml sausage
- Pail
- Drum

#### **STORAGE**

Store the sealant in closed original packaging. Store in dry premises at a temperature lower than 25°C (77°F). Expiration date is indicate on each container. Storage beyond the date specified on the container does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality insurance reasons. Contact our technical service.

#### CAUTION

Always consult sds before using the adhesive. For industrial use only. For more information, please contact your technical representative.



# **ADSEAL FC 4570 SERIES**

FAST NEUTRAL CURE SILICONE

## IMPORTANT

### **READ CAREFULLY**

The information and recommendations contained herein are derived from our research and information from other reliable sources. This data applies only to our products and not when used with other products. We believe in the reliability of our information. However, no guarantee is offered to that effect. It is the responsibility of the buyer to verify this data according to their own operating conditions to ensure that they conform to the purpose for which the product is intended, even before using it.

THE WARRANTY OFFERED BY ADFAST SHALL BE LIMITED TO THE REPLACEMENT OR REIMBURSEMENT OF THE PRODUCT IF THEY HAVE BEEN DEFECTIVE. NO OTHER IMPLIED OR EXPRESS WARRANTY APPLIES. ADFAST DISCLAIMS ANY OTHER LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.