

ADSEAL LM 4600 SERIES

WEATHERSEAL NEUTRAL CURE SILICONE SEALANT MAXIMUM ELONGATION

DESCRIPTION

ADSEAL LM 4600 SERIES is a one-component sealant/adhesive that vulcanizes as durable, elastic rubber silicone in contact with ambient humidity. Due to its rheological and non-sagging characteristics, it can be applied above the head, over the joints and on surfaces of vertical and horizontal walls. It is commonly used for sealing expansion and control joints, precast concrete panel joints, exterior insulation and finish system (EIFS) joints, curtain walls joints, mullion joints, and many other construction joints. ADSEAL LM 4600 SERIES adheres to glass, most types of wood, clean metals, silicone resins, ceramics, vulcanized silicone, synthetic and natural fibers and many painted surfaces (Validate with your representative) or certain plastics. Additionally, ADSEAL LM 4600 SERIES has an outstanding adhesion on alkaline materials, such as masonry, stone, concrete, granite and marble. The use of a primer might be necessary. Always perform a test before starting work.

ADSEAL LM 4600 SERIES CAN NOT BE PAINTED.

Due to its neutral vulcanization system, ADSEAL LM 4600 SERIES is used for caulking applications when a slower working time or an elongation of 100% and a compression of 50% are required. It does not give off any unpleasant odor during vulcanization and will not oxidize the metal. (Discoloration of copper-based metals may occur when sealed tightly). Due to its vulcanization system in contact with moisture, the depth of the bead should not exceed 13 mm (1/2"), otherwise the sealant cannot vulcanize completely. For applications with a bead depth of more than 13 mm, we recommend a two components silicone. Minimum movement joint size should be 1/4" x 1/4".

SPECIFICATION

- Meets ASTM C920, S, NS, Class 100/50 (excluding translucent version 4601), use NT, M, G, A, O
- Meets CAN/CGSB-19.18-M87
- V.O.C. emission **UL 1000612730-2046925**: CDPH/EHLB/Standard Method V1.2 (January 2017) "Standard Method for the Testing and Evaluation of Volatile Organic Chemical Emissions from Indoor Sources Using Environmental Chambers" (aka CA Section 01350). Reference LEED V4

LIMITATIONS

- Not designed for permanent immersion joints
- Not designed for structural applications
- Where the sealant is encapsulated and does not have access to ambient humidity
- In contact with strongly acidic or alkaline products
- Not designed for sealing horizontal traffic joints
- Joint less than 1/4" (6 mm) wide and deep

PHYSICAL PROPERTIES

Uncured	
Appearance	Pasty
Color	Available in a wide variety of colors
Density	1.19 g/ml
Extrusion rate (20 psi/diamètre 5mm)	75 – 300 g/min
Tack free time	55 – 65 minutes at 23°C (73°F) 50% r.h.
Slump (ASTM D2202)	None
V.O.C.	94 g/L (7.8%)
Shelf life	24 mois

ADSEAL LM 4600 SERIES

WEATHERSEAL NEUTRAL CURE SILICONE SEALANT MAXIMUM ELONGATION

Cured	
Hardness (ASTM C661)	28 – 30 (shore A)
Heat aging (ASTM C792)	6.8% (maximum 10% according to ASTM D5893 requirement)
Peel strength (ASTM C794)	36 lb / in.
Elongation at break (ASTM D412)	1558%
Maximum Tensile strength (ASTM D412)	223 psi
Tensile strength at 150% elongation (ASTM D412)	37 psi
Movement capability (ASTM C719)	+100% / -50% (excluding translucent version 4601)
Ultimate tensile adhesion (ASTM C1135)	93 psi
Maximum elongation (ASTM C1135)	743%
Tensile adhesion at 25% (ASTM C1135)	19 psi
Tensile adhesion at 50% (ASTM C1135)	26 psi
Tensile adhesion at 100% (ASTM C11350)	33 psi
Staining on porous surfaces (ASTM C1248)	None
Lap shear (aluminum)	91 psi (cohesive) / shifting 0.61 inch
Tensile adhesion when used in exterior insulation and finish systems (EIFS) joints (ASTM C1382) with Adseal Primer MK60095 (no failure in all cases)	<p>at 23°C (73°F) 50% r.h tensile strength @10% elongation = 11 psi tensile strength @25% elongation = 20 psi tensile strength @50% elongation = 28 psi tensile strength @100% elongation = 40 psi</p> <p>After 7 days of water immersion tensile strength @10% elongation = 11 psi tensile strength @25% elongation = 19 psi tensile strength @50% elongation = 25 psi tensile strength @ 100% elongation = 35 psi</p> <p>after 24 hours at -18°C (0°F) tensile strength @10% elongation = 12 psi tensile strength @25% elongation = 19 psi tensile strength @50% elongation = 26 psi tensile strength @100% elongation = 38 psi</p> <p>after 24 hours at 70°C (160°F) tensile strength @10% elongation = 11 psi tensile strength @25% elongation = 19 psi tensile strength @50% elongation = 26 psi tensile strength @100% elongation = 38 psi</p> <p>after 2500 hours UV conditioning tensile strength @10% elongation = 15 psi tensile strength @25% elongation = 24 psi tensile strength @50% elongation = 32 psi tensile strength @100% elongation = 43 psi</p>

ADSEAL LM 4600 SERIES**WEATHERSEAL NEUTRAL CURE SILICONE SEALANT MAXIMUM ELONGATION****APPLICATION****Construction**

- Expansion joints (masonry) (test with and without using primer before doing the complete work)
- EIFS (Exterior insulation and finish system)
- Perimeter construction joints
- Corner block or internal parts of curtain wall

Industrial

- Transportation vehicles
- Manufactured doors and windows
- Sealing of trailers and truck cabs
- Sealing cabins and marine windows

SURFACE PREPARATION

Surface must be free of dust, oil, grease, frost or any other contaminant. On porous surface, first use mechanical tool such as grinder to remove old sealant or any other contaminant. Use ADSEAL CLEANER 6003 to clean all surfaces. Let it evaporate 20 minutes before sealant application. Ensure that the backer rod ADSEAL BACKER ROD is friction fitted properly and ADSEAL PRIMER MK60095 have been applied if necessary. When using ADSEAL PRIMER MK60095, let the primer evaporate for 20 minutes prior to ADSEAL LM 4600 SERIES application. For more details consult the technical document: Application procedure for sealant movement and waterproofing joints.

METHOD OF USE

ADSEAL LM 4600 SERIES is easy to apply with a conventional manual, electric or pneumatic applicator (do not exceed 45 psi for a cartridge). Shape the sealant bead with the ADSEAL TOOLING KIT before skin formation. In order to facilitate the work, the shaping can be done with a solution of 5% clear dish soap and 95% water. Dip the ADSEAL TOOLING KIT into the solution. Avoid applying solution directly to the sealant. The use of this solution may reduce sealant adhesion if used in an abusive manner. Uncured sealant can be clean with a solvent such as mineral spirit. Bead surface contact should be at least 1/4". ADSEAL LM 4600 SERIES can be applied at temperatures as low as -20°F (-29°C). For more details consult the technical document: Application procedure for sealant movement and waterproofing joints.

TEMPERATURE APPLICATION

Sealants from the ADSEAL product line can be applied throughout the year, even in winter, unlike organic sealants such as polyurethanes, thermoplastics or any solvent-based adhesives or sealants. Never apply

ADSEAL LM 4600 SERIES**WEATHERSEAL NEUTRAL CURE SILICONE SEALANT MAXIMUM ELONGATION**

sealant in weather conditions where condensation or precipitation exists such as rainfall, freezing rain, snow or intense fog. Make sure the surface is free of frost. The temperature of the silicone sealant must be the same as the substrates. Avoid applying a warm sealant to a cold surface. The lower the temperature, the longer the sealant will take to vulcanize.

***** Beware of large fluctuations in temperature especially below freezing point. For example, when temperatures reach well below freezing point in a short period of time, the substrates may have a large elongation/compression movement. The sealant will not have enough time to form a fairly thick skin, which in some cases, may cause a breakage or wrinkling at the joint. If such phenomenon occurs, proceed with an adhesion test.**

PACKAGING

- 304ml cartridge
- 600ml sausage
- Pail
- Drum

STORAGE

Store the sealant in closed original packaging. Store in dry premises at a temperature lower than 25°C (77°F). Expiration date is indicated on each container. Storage beyond the date specified on the container does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality insurance reasons. Contact our technical service.

CAUTION

Always consult sds before using the product. Apply usual hygienic rules. Always test the product on your application before use. For industrial use only. For more information, please contact your technical representative.

IMPORTANT**READ CAREFULLY**

The information and recommendations contained herein are derived from our research and information from other reliable sources. This data applies only to our products and not when used with other products. We believe in the reliability of our information. However, no guarantee is offered to that effect. It is the responsibility of the buyer to verify this data according to their own operating conditions to ensure that they conform to the purpose for which the product is intended, even before using it.

THE WARRANTY OFFERED BY ADFAST SHALL BE LIMITED TO THE REPLACEMENT OR REIMBURSEMENT OF THE PRODUCT IF THEY HAVE BEEN DEFECTIVE. NO OTHER IMPLIED OR EXPRESS WARRANTY APPLIES. ADFAST DISCLAIMS ANY OTHER LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

ADSEAL LM 4600 SERIES**WEATHERSEAL NEUTRAL CURE SILICONE SEALANT MAXIMUM ELONGATION**