

ADBOND 5645 SERIES

Liquid polyurethane mono-component adhesive

DESCRIPTION

ADBOND 5645 SERIES is a liquid polyurethane mono-component adhesive that vulcanise with moisture. ADBOND 5645 SERIES is use to bond rigid insulation polyurethane foam, expanded or extruded polystyrene, wood, metal, cardboard honeycomb, particle panel, mdf, or certain plastics. Used for bonding between two flexible materials or a flexible and a rigid material. Never used for bonding two rigid materials. Some grades of ADBOND SERIES 5645 can be used in cold press or hot press.

PHYSICAL PROPERTIES

25°C (77°F) – 50% H.R.	
Color	Amber or red
Viscosity	1500 – 3000 cPs
Ph	2.5 – 4.5
Specific gravity	1.115 (kg/L) ±0.005
Solids content	> 99%
Cold resistance (uncured)	Protect from freezing (Possible reversibility)
V.O.C.	Refer to chart below
Open time	Refer to chart below
Press time	Refer to chart below

OPEN TIME, PRESS TIME, V.O.C. AND SHELF LIFE CHART

	5645X	5645A	5645B	5645C	5645E	5645G
Open time at 25°C (77°F) – 50% H.R.)	1 – 3.5 min.	5 – 10 min.	15 – 30 min.	30 – 60 min.	2 – 5 min.	60 – 180 min.
Press time at 25°C (77°F) – 50% H.R.	6 min.	20 min.	40 min.	60 min.	12 min.	120 min.
Press time at 40°C (104°F) – 50% H.R.	n/a	10 min.	20 min.	30 min.	n/a	60 min.
Press time at 70°C (158°F) – 50% H.R.	n/a	n/a	5 – 6 min.	6 – 7 min.	n/a	n/a
Press time at 80°C (176°F) – 50% H.R.	n/a	n/a	4 – 5 min.	5 – 6 min.	n/a	n/a
Full cure	24 hours	24 hours	24 hours	24 hours	24 hours	24 hours
V.O.C.	13.41 g/L	3.82 g/L	1.96 g/L	1.29 g/L	6.09 g/L	0.43 g/L
Shelf life	3 months	3 months	6 months	6 months	3 months	9 months

METHOD OF USE

ADBOND 5645 SERIES can be applied using compressible bottle, roller, manifold or mechanical roller. For optimum results the adhesive should be applied at a temperature of 18°C (65°F) to 25°C (77°F). It is recommended to apply 100 to

ADBOND 5645 SERIES

Liquid polyurethane mono-component adhesive

150 g / m² of adhesive (depending on the porosity or nature of the substrates) and then spray a mist of water (10% of the adhesive weight) over the adhesive before substrates assembly and put it under pressure. It is strongly advised to install a thermometer / hygrometer near the assembly station. Consult our technical department for more information.

APPLICATION

- Commercial steel doors assembly
- Sandwich panels
- Lamination
- Hard wood assembly
- Cold or hot press

CLEANING

For cleaning the mechanical rollers, first use the ADSOLV DP60011 to remove as much adhesive as possible by rotating the mechanical rollers in reverse. Then clean thoroughly with the ADSOLV 6040. For manifold systems cover the nozzles with hydraulic oil to completely block moisture infiltration. For any other equipment clean before curing of the product with the ADSOLV 6040. Cleaning solvents must be recovered and sent to an accredited company for the destruction of hazardous materials. For more information consult our technical department.

PACKAGING

- 18.9 liters pail
- 220 kg drum
- 1100 kg tote tank

STORAGE

The adhesive has a shelf life from 3 to 9 months from production date depending on different grade (refer to chart above), in the original closed container and stored in a cool, dry place (10 ° C to 25 ° C). Protect from frost. Keep container tightly closed to prevent contamination. Open container has to be protected from moisture with nitrogen or desiccant.

CAUTION

Always consult sds before using the adhesive. Apply usual hygienic rules. For industrial use only. For more information, please contact your technical representative.

ADBOND 5645 SERIES
Liquid polyurethane mono-component adhesive**IMPORTANT****READ CAREFULLY**

The information and recommendations contained herein are derived from our research and information from other reliable sources. This data applies only to our products and not when used with other products. We believe in the reliability of our information. However, no guarantee is offered to that effect. It is the responsibility of the buyer to verify this data according to their own operating conditions to ensure that they conform to the purpose for which the product is intended, even before using it.

THE WARRANTY OFFERED BY ADFAST SHALL BE LIMITED TO THE REPLACEMENT OR REIMBURSEMENT OF THE PRODUCT IF THEY HAVE BEEN DEFECTIVE. NO OTHER IMPLIED OR EXPRESS WARRANTY APPLIES. ADFAST DISCLAIMS ANY OTHER LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.