

## ADSEAL IG 4500 SERIES

### ULTRA-LOW MIGRATION NEUTRAL CURE SILICONE SEALANT

#### DESCRIPTION

ADSEAL IG SERIES 4500 is an ultra-low migration, non-corrosive 100% silicone adhesive sealant designed for back bedding joints. It offers a good initial grip and fast drying. It can be used for window manufacturing as well as other industrial applications. It offers excellent adhesion on aluminum, glass, wood, some plastics including PVC, several types of metals and several painted surfaces (validate with your technical representative). Always perform an adhesion test before starting work. It is compatible with a wide variety of sealed glass units and rubber gaskets. It has excellent weatherability and provides excellent durability. Due to its rheological and non-sag characteristics, it can be applied above the head, as well as vertical or horizontal surfaces.

ADSEAL IG 4500 SERIES CAN NOT BE PAINTED.

Due to its neutral vulcanization system, ADSEAL IG 4500 SERIES is used for caulking applications or when a faster working time is required. ADSEAL IG 4500 SERIES is also used for general sealing, caulking and electrical insulation applications. It does not give off any unpleasant odor during vulcanization and will not oxidize the metal (discoloration of copper-based metals may occur when sealed tightly). Due to its curing system in contact with moisture, the depth of the bead should not exceed 13 mm (1/2 "), otherwise the sealant cannot cure completely. For applications with a bead depth of more than 13 mm, we recommend a two components silicone. Minimum movement joint size should be 1/4" x 1/4".

#### SPECIFICATIONS

- Meets CAN / CGSB standards 19.13-M87
- Meets ASTM C920, type S, NS grade, use NT, G, A, O.
- Meets AAMA 802.3 et 805.2 standards
- Meets American Federal Specifications TT-S-1543A, class A and TT-S-00230C, class A, type II
- 

#### LIMITATIONS

- Not designed for permanent immersion joints
- Where the sealant is encapsulated and does not have access to ambient humidity
- In contact with strongly acidic or alkaline products
- Not designed for sealing horizontal traffic joints
- Not recommended for movement joint less than 1/4 " or 6 mm. (width and depth)
- 

#### PHYSICAL PROPERTIES

Uncured at 23°C (73°F) / 50% R.H.	
Appearance	Paste
Color	4501 (translucent), 4502 (white), 4503 (black) Special colors upon request.
Density	1.012
V.O.C.	67 g/L
Extrusion rate (20 psi/diameter 5mm)	45 g/min

**ADSEAL IG 4500 SERIES****ULTRA-LOW MIGRATION NEUTRAL CURE SILICONE SEALANT**

Tack free time (ASTM C679)	10 minutes
Rheological properties (ASTM C639)	No sagging
Shelf life	12 months

**Cured 21 days at 23°C (73°F) / 50% R.H.**

Hardness (ASTM D2240)	32 shore A
Elongation at break (ASTM D412)	650%
Maximum Tensile strength (ASTM D412)	194psi
Lap shear (ASTM C961)	69psi
Peel adhesion (ASTM C794)	15 pli

**APPLICATION**

- Back bedding for doors and windows
- Windows and doors manufacturing
- 

**SURFACE PREPARATION**

Surfaces must be free of dust, grease, frost, or any other contaminant. Clean surfaces with ADSEAL CLEANER 6003. Allow to evaporate for 20 minutes before applying ADSEALIG 4500. For porous surfaces, mechanical cleaning may be necessary during repair work. In some cases, ADSEAL IG 4500 may require the use of a primer. If this is the case, use ADSEAL PRIMER. For the complete procedure and the type of primer to use, consult our [ADSEAL PRIMER Guide](#). The use of ADSEAL BACKER ROD is recommended for a movement joint. If there is insufficient space for the use of backer rod, we strongly suggest the use of non-stick tape. For more information, consult your technical representative.

**METHOD OF USE**

ADSEAL IG 4500 SERIES is easy to apply with a conventional manual, electric or pneumatic applicator (do not exceed 45psi for a cartridge). If necessary, shape the sealant bead with the ADSEAL TOOLING KIT before skin formation. In order, to facilitate the work, the shaping can be done with a solution of 5% clear dish soap and 95% water. Dip the ADSEAL TOOLING KIT into the solution. Avoid applying solution directly to the sealant. The use of this solution may reduce sealant adhesion if used in an abusive manner. Uncured sealant can be clean with a solvent such as mineral spirit.

**TEMPERATURE APPLICATION**

Sealants from the **ADSEAL** product line can be applied throughout the year, even in winter, unlike organic sealants such as polyurethanes, thermoplastics or any solvent-based adhesives or sealants. Never apply sealant in weather conditions where condensation or precipitation exists such as rainfall, freezing rain, snow, or intense fog. Make sure the surface is free of frost. The temperature of the silicone sealant must be the same as the substrates. Avoid applying a warm sealant to a cold surface. The lower the temperature, the longer the sealant will take to cure.

**ADSEAL IG 4500 SERIES****ULTRA-LOW MIGRATION NEUTRAL CURE SILICONE SEALANT**

\*\*\* Cure of the sealant occurs from the surface down and if the joint is moving during cure, due to large fluctuations in ambient temperature, there will be expansion and contraction of the material creating a risk of cracking or wrinkling / swelling at the surface of the joint.

To reduce this impact, it is recommended to:

- Use an open cell polyurethane backer rod to accelerate the curing of the sealant.
- Install the sealant at the average daily temperature to reduce daily movement.
- Ensure that the joint depth does not exceed a ratio of 2:1 or 12 mm (1/2") maximum.
- The use of a primer can accelerates the development of the adhesion. Although not necessarily recommended, this step can help establish the success of the project if there is excessive movement of the joint during cure.

**PACKAGING**

- 304ml cartridge
- 400 ml and 600ml sausage
- Drum

**STORAGE**

Store the sealant in closed original packaging. Store in dry premises at a temperature between 8°C (46°F) and 25°C (77°F). High humidity and storage below or above these temperatures will shorten shelf life. Expiration date is indicated on each container. Storage beyond the date specified on the container does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality insurance reasons. Contact our technical service.

**CAUTION**

Always consult SDS (Safety Data Sheet) before using the product. Apply usual hygienic rules. Always test the product on your application before use. For industrial use only. For more information, please contact your technical representative.

**IMPORTANT****READ CAREFULLY**

The information and recommendations contained herein are derived from our research and information from other reliable sources. This data applies only to our products and not when used with other products. We believe in the reliability of our information. However, no guarantee is offered to that effect. It is the responsibility of the buyer to verify this data according to their own operating conditions to ensure that they conform to the purpose for which the product is intended, even before using it.

**THE WARRANTY OFFERED BY ADFAST SHALL BE LIMITED TO THE REPLACEMENT OR REIMBURSEMENT OF THE PRODUCT IF THEY HAVE BEEN DEFECTIVE. NO OTHER IMPLIED OR EXPRESS WARRANTY APPLIES. ADFAST DISCLAIMS ANY OTHER LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.**